

STOVING ALKYD TOP COAT COLOR MSV – 24 - 00

Product Information

GYUNG DO PAINT

This product is 1 components stoving alkyd top coat color based on alkyd resin, amino resin.

It has good hardness, curing.

Recommended Use

For steel

Technical Data

Appearance	Viscous White Liquid
Sp. Gr. (gr/cm³, 32°C)	1.1~1.2
Drying Time (32°C)	150°C x 30 min.
Application	Spray
Spray Viscosity (NK2,32°c)	11~13
Theoretical Coverage	10 m²/lt (DFT 40μm, WET 100μm)
Thinner	Stoving Thinner
Gloss (60°)	Full gloss
Flash Point (°C)	About 25
Solid Content (%)	55±1

Surface Preparation

Remove oil, water, and dust.

Precaution

1. After application, close the container tightly.